

Classification

EN ISO 14343-A: B 19 9 L

EN ISO 14343-B: BS 308L

AWS A5.9: EQ 308L

Chemical analysis (Typical values in %)

C	Mn	Si	Cr	Ni
0.01	1.9	0.4	20	10.5

Storage

Keep dry, avoid condensation, dust and oil traces