

Classification

EN ISO 14343-A: B 22 11 L

EN ISO 14343-B: BS 309LD

AWS A5.9: ~EQ 309L

Chemical analysis (Typical values in %)

C	Mn	Si	Cr	Ni
0.015	1.8	0.3	21.1	11.4

Storage

keep dry, avoid condensation, dust and oil traces