

Classification

EN ISO	14343-A: B 23 13 L
EN ISO	14343-B: BS 309L
AWS	A5.9: EQ 309L

Chemical analysis (Typical values in %)

C	Mn	Si	Cr	Ni
0.01	1.8	0.4	23.6	13.3

Storage

keep dry, avoid condensation, dust and oil traces